

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A block copolymer composition which is a block copolymer composition comprising, as monomer units, from 55 to 95 mass% of a vinyl aromatic hydrocarbon and from 5 to 45 mass% of a conjugated diene, ~~characterized in that it~~ which composition contains the following components A and B in a blend ratio within a range of component A/component B = 20 to 80/80 to 20 (mass ratio):

Component A is a block copolymer


- (1) which comprises, as monomer units, from 55 to 95 mass% of a vinyl aromatic hydrocarbon and from 5 to 45 mass% of a conjugated diene,
- (2) which is constituted by a hard segment block made mainly of the vinyl aromatic hydrocarbon and a soft segment block made mainly of the conjugated diene,
- (3) wherein the hard segment block comprises blocks S1 and S2 made mainly of a vinyl aromatic hydrocarbon having two types of different molecular weights, and when the number average molecular weights of S1 and S2 are represented by M1 and M2, respectively, M1 is within a range of from 75,000 to 170,000 and M2 is within a range of from 14,000 to 30,000, and their ratio M1/M2 is within a range of from 4 to 9, and the ratio of S1 to S2 is within a range of S1/S2 = 6 to 35/65 to 94 (molar ratio), and
- (4) which is produced by a coupling reaction; and

component B is a block copolymer


- (1) which comprises, as monomer units, from 55 to 95 mass% of a vinyl aromatic hydrocarbon and from 5 to 45 mass% of a conjugated diene,
- (2) which is constituted by a hard segment block made mainly of the vinyl aromatic hydrocarbon and a soft segment block made mainly of the conjugated diene,

- (3) wherein the hard segment block comprises blocks S3 and S4 made mainly of a vinyl aromatic hydrocarbon having two types of different molecular weights, and when the number average molecular weights of S3 and S4 are represented by M3 and M4, respectively, M3 is within a range of from 80,000 to 160,000 and M4 is within a range of from 4,000 to 12,000 and their ratio M3/M4 is within a range of from 13 to 22, and the ratio of S3 to S4 is within a range of $S3/S4 = 5$ to 30/70 to 95 (molar ratio), and
- (4) which is produced by a coupling reaction.

Claim 2 (Original): The block copolymer composition according to Claim 1, wherein component A is a mixture of three types of block copolymers as identified in the following (1), and component (B) is a mixture of three types of block copolymers as identified in the following (2):



(wherein each of S1 and S2 represents a hard segment block made mainly of a vinyl aromatic hydrocarbon, B1 represents a soft segment block made mainly of a conjugated diene, the number average molecular weight of B1 is within a range of from 10,000 to 30,000, X is a residual group of a coupling agent, each of i and m is an integer of 0 or more, and i+m is at least 1 and at most 8);



(wherein each of S3 and S4 is a hard segment block made mainly of a vinyl aromatic hydrocarbon, B2 represents a soft segment block made mainly of a conjugated diene, the number average molecular weight of B2 is within a range of from 9,000 to 20,000, Y is a residual group of a coupling agent, each of n and o is an integer of 0 or more, and n+o is at least 1 and at most 8).

Claim 3 (Currently Amended): The block copolymer composition according to Claim 1 ~~[[or 2]]~~, wherein components A and B are block copolymers obtained by coupling by means of an epoxidized oil.

Claim 4 (Original): The block copolymer composition according to Claim 3, wherein the epoxidized oil is epoxidized soybean oil.

Claim 5 (Currently Amended): The block copolymer composition according to Claim 3 ~~[[or 4]]~~, ~~characterized in that~~ wherein the ratio of the molar amount of residual groups of ring opened epoxy groups present in the epoxidized oil residual groups in the block copolymer composition comprising components A and B is less than 0.7 to the molar amount of the total of epoxy groups and said residual groups of ring opened epoxy groups, present in the epoxidized oil residual groups.

Claim 6 (Currently Amended): The block copolymer composition according to ~~any one of Claims 1 to 5~~ Claim 1, wherein components A and B are mixed in a solution state.

Claim 7 (Currently Amended): A thermoplastic resin composition comprising the block copolymer composition as ~~defined in any one of Claims 1 to 6~~ according to Claim 1, and another thermoplastic resin.

Claim 8 (Currently Amended): A molded product made of the block copolymer composition according to Claim 1 as ~~defined in any one of Claims 1 to 6, or the thermoplastic resin composition as defined in Claim 7.~~

Claim 9 (New): The block copolymer composition according to Claim 2, wherein components A and B are block copolymers obtained by coupling by means of an epoxidized oil.

Claim 10 (New): The block copolymer composition according to Claim 9, wherein the epoxidized oil is epoxidized soybean oil.

Claim 11 (New): The block copolymer composition according to Claim 4, wherein the ratio of the molar amount of residual groups of ring opened epoxy groups present in the epoxidized oil residual groups in the block copolymer composition comprising components A and B is less than 0.7 to the molar amount of the total of epoxy groups and said residual groups of ring opened epoxy groups, present in the epoxidized oil residual groups.

Claim 12 (New): The block copolymer composition according to Claim 9, wherein the ratio of the molar amount of residual groups of ring opened epoxy groups present in the epoxidized oil residual groups in the block copolymer composition comprising components A and B is less than 0.7 to the molar amount of the total of epoxy groups and said residual groups of ring opened epoxy groups, present in the epoxidized oil residual groups.

Claim 13 (New): The block copolymer composition according to Claim 10, wherein the ratio of the molar amount of residual groups of ring opened epoxy groups present in the epoxidized oil residual groups in the block copolymer composition comprising components A and B is less than 0.7 to the molar amount of the total of epoxy groups and said residual groups of ring opened epoxy groups, present in the epoxidized oil residual groups.

Claim 14 (New): A molded product made of the thermoplastic resin composition according to Claim 7.